

# THE INFLUENCE OF INK CONCENTRATION AND LAYER THICKNESS ON YELLOW COLOUR REPRODUCTION IN LIQUID ELECTROPHOTOGRAPHY TONER

**Igor Majnarić, Aleš Hladnik, Tadeja Muck, Ivana Bolanča Mirković**

Original scientific paper

In liquid toner electrophotography, colour gamut is often diminished in the yellow region leading to problems with photo quality prints. It is known that the concentration of pigment particles in the printing ink and its thickness when applied on a paper substrate decisively influence final print quality. Variation of these two parameters for the yellow process ink was performed by modifying the printing process of the electrophotographic printer HP Indigo S1000. Printed colour patches of ECI test chart were analysed colorimetrically and using image analysis approach. Two-way analysis of variance was implemented to statistically assess the obtained results. Both studied responses – colour gamut volume and area coverage of halftone dots – were found to be primarily influenced by the yellow ink layer thickness and much less by the ink concentration. Increase from one to two ink layers had a significantly stronger effect on each of the two responses when compared to an additional increase from two to three layers.

**Keywords:** colour gamut; colour reproduction; halftone dots; liquid toner electrophotography; print quality; tone value

## Utjecaj koncentracije bojila i debljine nanosa žute na kolornu reprodukciju s tekućim elektrofotografskim tonerom

Izvorni znanstveni članak

U elektrofotografiji s tekućem tonerom, kolornigamut je često smanjen u žutom području što vodi do problema pri realizaciji otiska fotografske kvalitete. Poznato je da koncentracija čestica pigmenta u tiskarskom bojilu i debljina nanosa na papirnatoj podlozi utječe na konačnu kvalitetu otiska. U ovom radu varirana su upravo ta dva parametra, primjenjujući pritom žuto ElectroInk procesno bojilo te elektrofotografski tiskarski stroj HP Indigo. Za kolorimetrijsku i slikovnu analizu primjenjena je ECI tiskovna forma koja sadrži 378 definiranih polja. Dobiveni rezultati statistički su obrađeni metodom dvosmjerne analize varijacija. Studija je prikazana pomoću volumena kolornog gamuta, te površinske pokrivenosti rasterskih elemenata (točkica). U radu je utvrđeno je da na kvalitetu obojenja prvenstveno utječe debljina nanosa žutog bojila, dok je utjecaj koncentracije žutih pigmenata minoran. Povećanje nanosa bojila sa jedanog na dva imalo je mnogo jači učinak od onog koji je realiziran povećanjem sa dva sloja na tri sloja.

**Ključne riječi:** elektrofotografski tekući toner; koloni gamut; kolorna reprodukcija; kvaliteta otiska; rasterske točke; tonska vrijednost

## 1 Introduction

In obtaining a high-quality colour reproduction, process printing inks (CMYK) and especially their colorants – pigments or dyes – play a decisive role. Ink formulation and the amount of ink being used must meet the requirements of the actual printing technology. In particular, concentration of pigment particles in the yellow ink as well as the final layer thickness of the ink applied to the printing substrate can be varied by a printer to assure the desired reproduction of lighter tones.

The aim of this study was to examine the technological possibilities and limitations related to the use of the yellow process ink within the electrophotographic printing system with the liquid toner – also known as HP ElectroInk. The results should also provide some directions on how to improve the reproduction of yellow colour, obtain higher colour saturation, and consequently, to achieve higher print quality with larger colour gamut.

During the printing process, to attain a larger colour gamut it is common to apply a higher amount of the colorant onto the printing substrate. Technically, this can be accomplished in one of two ways: either by increasing the concentration of the pigmented toner particles in ink or by increasing the number of ink layers.

## 2 Liquid electrophotography toner

The development process in the liquid toner electrophotography is very complicated and consists of several consecutive steps [1]. The final ink layer thickness is primarily influenced by the voltages of the developer

drum and the developer rollers. By varying individual voltages, higher colour saturation in prints can be obtained [2].

ElectroInk contains charged pigmented toner particles in a liquid carrier. Similarly to other digital printing technologies, such as dry electrophotography, printing is performed via electrically controlling the location of the toner particles. In its basic state the ink is an emulsion consisting of pigments in a form of a thermal polymer (24-29%), which is dispersed in a non-polar volatile oil (70-75%). The ink also contains additives for increasing the conductivity (about 10 %) [3]. ElectroInk is supplied as a concentrated paste that is loaded into the press in tubular cartridges. Inside the press it is fed into ink supply tanks and diluted with oil, to form a fluid mixture ready for printing.

During the printing process, the ElectroInk structure rapidly alters. Ink viscosity increases due to a high temperature ( $\theta = 125^{\circ}\text{C}$ ) and loss of the volatile solvent. By heating the thermal polymer, the process of plasticity begins causing the polymer to become suitable for adhering to the printing substrate [4].

Particles of the yellow thermal toner have a characteristic fluffy shape with the size ranging from 1 to 5  $\mu\text{m}$  [5, 6]. Such a shape serves primarily to ease the binding of the conductivity-increasing additives. These polar additives adhere to the pigmented toner particles with their positively charged molecular groups. The particles are then ready to move towards a more positive electrostatic field, i.e. a field with a lower negative charge [7, 8, 9].


Further ink film thickness increase on the printing substrate is possible by means of an overprinting. Such a

possibility exists only with satellite electrophotographic machines in which one printing unit is used for printing several inks [10, 11, 12, 13]. In this case the printing is done on the already printed (dried) ink layer.

### 3 Experimental part

For the experiment we used ECI test chart (target) with 378 colour patches. The chart was printed with the electrophotographic machine HP Indigo S1000 (resolution:  $812 \times 812$  dpi). The printer normally uses four process inks (CMYK) of which the yellow one was modified for the purpose of our study. This (Yellow 74) is an azo-based compound (Dalamar yellow C. I. 11741) with the chemical formula  $C_{18}H_{18}N_4O_6$ . The printing substrate was a calandered paper with the grammage of  $280\text{ g/m}^2$ .

By adding various amounts of the pigment, three yellow ink concentrations (C) were prepared –  $C1=1,28$ ;  $C2=1,61$  and  $C3=1,98$  – characterized by different ink densities as measured by the portable ink density meter EAS-1120-53 that was developed by HP Indigo. In addition, the repetition of individual yellow colour separations was accomplished. In this way YMCK (with one yellow layer; L1), YYMCK (with two yellow layers; L2) and YYYMCK prints (with three yellow layers; L3) were made. Consequently, nine different combinations of yellow ink concentration-ink layer thickness were investigated as schematically displayed in Fig. 1.




**Figure 1** Left: Design of experiments; three yellow ink concentrations ( $C1, C2, C3$ ) combined with different numbers of yellow ink layers (L1, L2, L3). Top: Total workflow of the study.

Printed colour patches were examined by spectrophotometer X-rite DTP 20 using  $0/45^\circ$  measuring geometry. The obtained  $L^*a^*b^*$  values were used for the calculation of colour differences (CIE LAB delta E2000) and colour gamut volumes (Monaco Profiler Platinum Version). Digital images of the printed halftone dots were obtained by Leica DR 2400 optical microscope with a built-in 1,3 megapixels Dinolite camera. Subsequent

image analysis was performed by means of ImageJ software [14, 15, 16]. All major processing steps of our study are presented in Fig. 1.

### 4 Results and discussion

Colorimetric data for the 378 printed colour patches enabled calculations of colour gamut volumes for each of the nine ink concentration – ink layer thickness combinations. CIE  $a^*b^*$  diagrams for the three typical lightness ( $L^*$ ) values are displayed in Figs. 2 and 3.



**Figure 2** 2D colour gamuts for test chart patches printed with different concentrations and constant number of layers (= two; L2) shown for  $L^* = 20$  (top),  $L^* = 50$  (middle) and  $L^* = 80$  (bottom).




Figure 3 2D colour gamuts for test chart patches printed with different numbers of layers and constant ink concentration (= C2) shown for  $L^* = 20$  (top),  $L^* = 50$  (middle) and  $L^* = 80$  (bottom).

During printing, the simplest control parameter for halftone value transfer is the measurement of the dot percentage in the halftone patches of the ECI test chart. Variation of the two investigated parameters – yellow ink concentration and ink layer thickness – directly affected the appearance and characteristics of the halftone dots and, consequently, caused the tone value increase (dot gain). Yellow halftone patches at 50 % A (tone value) were subsequently analysed. Fig. 4 shows six typical halftone yellow patches at 50 % A.




Figure 4 Yellow halftone patches at 50 % A (magnification: 60 $\times$ ).

Yellow halftone patches at 50 % A were further processed using image analysis approach. Each imaged printed patch was converted into a grayscale – and finally into a binary image using intensity thresholding (Otsu's method). Tone value – percentage of area covered by halftone dots – was calculated.

Two-way analysis of variance (ANOVA) results for colour gamut volume and area coverage at the 95 % confidence level are displayed in Tab. 1 and Tab. 2, respectively. Since five measurements were obtained for each of the nine ink concentration – layer thickness combinations, it was also possible to estimate the interaction effect between the two investigated parameters.




Figure 5 Effects of ink layer thickness (left) and ink concentration (right) on colour gamut volume of ECI test chart patches.


**Table 1** ANOVA table for colour gamut volume

Source	Sum of Squares	Df	Mean Square	F-Ratio	P-Value
MAIN EFFECTS					
A: Layer thickness	205 542	2	102 771	4033,26	0,0000
B: Ink concentration	729,136	2	364,568	14,31	0,0000
INTERACTIONS					
AB	275,306	4	68,8265	2,70	0,0458
RESIDUAL	917,311	36	25,4809		
TOTAL (CORRECTED)	207 464	44			


**Table 2** ANOVA table for area coverage

Source	Sum of Squares	Df	Mean Square	F-Ratio	P-Value
MAIN EFFECTS					
A:Layer thickness	1633,94	2	816,971	20,97	0,0000
B:Ink concentration	66,7897	2	33,3949	0,86	0,4328
INTERACTIONS					
AB	84,7066	4	21,1766	0,54	0,7047
RESIDUAL	1402,28	36	38,9523		
TOTAL (CORRECTED)	3187,72	44			

Means and 95.0 Percent LSD Intervals



Means and 95.0 Percent LSD Intervals

**Figure 6** Effects of ink layer thickness (left) and ink concentration (right) on area coverage in yellow halftone patches.

ANOVA results show that both layer thickness and ink concentration have statistically significant effects on color gamut volume at 95 % confidence level. Increasing the values of each of the two parameters results in a larger gamut volume (Fig. 5). Significance of the interaction effect ( $P$ -value  $< 0,05$ ) is almost exclusively due to the extremely large contribution of the first factor – layer thickness. On the other hand, tone value increase (dot gain) is only influenced by the number of yellow ink layers, i.e. layer thickness, while ink concentration has virtually no impact on this dependent variable (Tab. 2 and Fig. 6). It can be noticed that an increase in the number of ink layers from 1 to 2 has a much stronger effect on both dependent variables when compared to the further addition of the third layer (L2 → L3).

## 5 Conclusions

Our study suggests that a higher colour gamut volume in yellow colour region can be achieved primarily by multilayer printing, i.e. by increasing the number of yellow ink layers – especially from one to two – and much less by raising the concentration of the pigmented toner particles in the yellow ink. Such an increase in layer thickness, however, has a detrimental effect on the characteristics of the printed halftone dots, causing an undesirable tone value increase (dot gain). Multilayer printing increases the dynamic range but at the same time reduces bit depth of a printed image. Therefore, if we want to increase the colour gamut volume and preserve optimal dynamic range, it is recommended to use two layers printing only for reproducing solid yellow tones.

## Acknowledgements

This work was supported by the Ministry of Science, Education and Sports of the Republic of Croatia (New formulations of materials, features prints – code: 128-1281955-1953 and Study on technological factors of graphic design and the systematic improvement of quality - code: 128-1281955-1962).

## 6 References

- [1] Chatow, C.; Udi, C. The Fundamentals of Indigo's Digital Offset Colour Printing Process and How it Rivals Mechanical Offset Printing. // NIP18 Proceedings of International Conference on Digital Printing Technologies / San Diego, California, 2002, pp. 125-128.
- [2] Majnarić, I.; Bolanča, Z.; Bolanča Mirković, I. The Influence of the Developer Drum Voltage on Screen Dot Formation.// Proceedings of 20<sup>th</sup> International DAAAM Symposium "Intelligent Manufacturing & Automation Focus on Theory, Practice and Education". / Vienna, Austria, 2009, pp. 607-608.
- [3] Goldmann, G.; The World of Printers. Oce Printing Systems GmbH, Dusseldorf, Germany, 2004.
- [4] Majnarić, I.; Bolanča, I.; Bolanča, Z.; Milković, M. Condition in Digital Printing of Packaging on the Print Quality. // Proceedings of International Conference on Digital Production Printing and Industrial Applications. / Amsterdam, Niderland, 2005, pp. 97-99.

- [5] HP ElectroInk Frequently Asked Questions. 2013. URL: <http://www.thedigitalprinters.com/faq/assets/Electroink%20FAQ.pdf>. (5. 4. 2013.)
- [6] Aqua, T.; Salalha, W.; Reznik, S.; Zussman E. Experimental and Analytical Study of Dot Gain Between Elastic and Deformable Drums. // NIP29 Proceedings of the 29th International Conference on Digital Printing Technologies and Digital Fabrication / Seattle, Washington, 2013, pp. 72-74.
- [7] Kahatabi, R.; Salalha, W.; Forgacs, P.; Yacoub, N.; Avramov, D. Israel, H. I. Dielectric Properties Study of Thin Polymer Film Layers. // NIP28 Proceedings of the 28th International Conference on Digital Printing Technologies and Digital Fabrication / Quebec City, Canada, 2012, pp. 287-290.
- [8] Forgacs, P.; Teishev, A. Electro-Rheological Model of HP-Indigo ElectroInk. // NIP28 Proceedings of the 28<sup>th</sup> International Conference on Digital Printing Technologies and Digital Fabrication / Quebec City, Canada, 2012, pp. 348-351.
- [9] Forgacs, P. Theory of Ink Transfer in HP-Indigo Digital Press Machines. // NIP29 Proceedings of the 29<sup>th</sup> International Conference on Digital Printing Technologies and Digital Fabrication/ Seattle, Washington, 2013. pp. 429-432.
- [10] Rong, X.; Obispo, S. L. Quality Comparison of HP Indigo to Offset Lithography. // NIP25 Proceedings of 25<sup>th</sup> International Conference on Digital Printing Technologies and Digital Fabrication / Louisville, Kentucky, 2012, pp. 478-481.
- [11] Ruizhi, S.; Bing, S.; Xiao, Z.; Qiang, S. Tone Reproduction Characteristic of Digital Printing.// NIP28 Proceedings of the 28<sup>th</sup> International Conference on Digital Printing Technologies and Digital Fabrication / Quebec City, Canada, 2012, pp. 242-245.
- [12] Tagansky, B. HP-Indigo Technology and its Application to Photo Printing. // NIP28 Proceedings of the 28<sup>th</sup> International Conference on Digital Printing Technologies and Digital Fabrication / Quebec City, Canada, 2012, pp. 31-34.
- [13] Možina, K.; Medved, T.; Rat, B.; Bračko, S. Influence of Light on Typographic and Colorimetric Properties of Ink Jet Prints. // Journal of Imaging Science and Technology. 54, 6(2010), pp. 060403-060403-8.
- [14] Rasband, W. S. ImageJ. U. S. National Institutes of Health, Bethesda, Maryland, USA. 1997-2013. URL: <http://imagej.nih.gov/ij/> (16. 4. 2013.)
- [15] Dzik, P.; Furst, T.; Vesely, M.; Kacerova, S.; Stepankova, E.; Smejkalova, H. Image Permanence Evaluation by Color Gamut Volume Change. // Journal of Imaging Science and Technology. 56, 6(2012), pp. 060506-1- 060506-9.
- [16] Grilj, S.; Muck T., Gregor Svetec, D. The ageing resistance of offset and electrophotographic prints. // Nordic Pulp and Paper Research Journal. 27, 4(2012), pp. 739-749.

#### Authors' addresses

*Assist. Prof. dr. sc. Igor Majnarić*

University of Zagreb, Faculty of Graphic Arts,  
Getaldićeva 2, 10000 Zagreb, Croatia  
E-mail: majnaric@grf.hr

*Prof. dr. sc. Aleš Hladnik*

University of Ljubljana, Faculty of Natural Sciences and  
Engineering, Department of Textiles,  
Snežniška 5, 1000 Ljubljana, Slovenia  
E-mail: ales.hladnik@ntf.uni-lj.si

*Prof. dr. sc. Tadeja Muck*

University of Ljubljana, Faculty of Natural Sciences and  
Engineering, Department of Textiles,  
Snežniška 5, 1000 Ljubljana, Slovenia  
E-mail: tadeja.muck@gmail.com

*Assist. Prof. dr. sc. Ivana Bolanča Mirković*

University of Zagreb, Faculty of Graphic Arts,  
Getaldićeva 2, 10000 Zagreb, Croatia  
E-mail: ibolanca@grf.hr



## Location

Situated on the eastern coast of Spain, Valencia was founded in 138BC as a Roman colony. The city, which is the third largest in Spain, has the biggest port on the Mediterranean Sea. A large historic city centre makes Valencia a popular tourist destination with many ancient monuments, museums and sights of interest. Valencia is famous for "Les

Falles" – four days and nights of city wide celebrations held each year during March in commemoration of Saint Joseph. Visitors are also drawn to the region for its food with Paella having originated from the city.

## Conference Venue

The TRYP Valencia Oceanic Hotel is situated near the centre of Valencia. Only a short distance from the City of Arts and Sciences, the harbour and downtown, the hotel is close to all that the city has to offer. With 200 rooms all with high speed internet access, a 24 hour fitness centre, pool, sauna, bar and restaurant, the hotel has all the amenities guests may require.

## Submission Information

**Papers are invited on the topics outlined and others falling within the scope of the meeting. Abstracts of no more than 300 words should be submitted as soon as possible.**

Abstracts should clearly state the purpose, results and conclusions of the work to be described in the final paper. Final acceptance will be based on the full-length paper, which if accepted for publication must be presented at the conference.

The language of the conference will be English.

**Online submission:**  
[wessex.ac.uk/air2015](http://wessex.ac.uk/air2015)

**Email submission:**  
imoreno@wessex.ac.uk

**Submit your abstract with 'Air Pollution 2015' in the subject line.**

Please include your name, full address and conference topic.

## Conference Secretariat

Irene Moreno Milán

imoreno@wessex.ac.uk

Wessex Institute  
Ashurst Lodge, Ashurst  
Southampton, SO40 7AA, UK

Tel: +44 (0) 238 029 3223

Fax: +44 (0) 238 029 2853

For more information visit:  
[wessex.ac.uk/air2015](http://wessex.ac.uk/air2015)



Air Pollution 2015 is the 23rd Annual Meeting in the successful series of international conferences organised by the Wessex Institute dealing with Modelling, Monitoring and Management of Air Pollution.

The series started in Mexico (1993) and continued in Barcelona (1994); Halkidiki (1995); Toulouse (1996); Bologna (1997); Genova (1998); San Francisco (1999); Genova (1999); Ancona (2001); Segovia (2002); Catania (2003); Rhodes (2004); Cordoba (2005); New Forest (2006); Algarve (2007); Skiathos (2008); Tallinn (2009); Kos (2010) Malta (2011), A Coruna (2012), Siena (2013) and Split (2014). These meetings have attracted outstanding contributions from leading researchers from around the world. The papers selected for presentation and included in the Conference Proceedings have been permanently stored in the WIT eLibrary as Transactions of the Wessex Institute (see <http://library.witpress.com>). These collected papers provide an invaluable record of the development of science and policy pertaining to air pollution. The conferences in this series have discussed and considered many important air pollution issues and the international nature of the attendees has ensured that the conference findings and conclusions enjoy a wide and rapid dissemination amongst the air pollution science and policy communities. Air pollution issues remain one of the most challenging problems facing the international community. The series has demonstrated the wide spread nature of the air pollution phenomena and has explored in depth the impacts of air pollution on human health and the environment.

The series also recognised, at a very early stage, that science alone will not improve a polluted atmosphere. The scientific knowledge derived from well designed studies needs to be allied with further technical and economic studies in order to ensure cost effective and efficient mitigation. In turn, the science, technology and economic outcomes are necessary but not sufficient. Increasingly, the conference has recognised that the outcome of such research needs to be contextualised within well formulated communication strategies that help policy makers and citizens to understand and appreciate the risks and rewards arising from air pollution management. Consequently, the series has enjoyed a wide range of high

quality papers that develop the fundamental science of air pollution and an equally impressive range of presentations that places these new developments within the frame of mitigation and management of air pollution. This important conference brings together contributions from scientists from around the world to present recent work on various aspects of air pollution phenomena. Notable in each of the conferences in this series has been the opportunity to foster scientific exchange between participants. New collaborations amongst scientists, and between scientists and policy makers or regulators have arisen through contacts made in this series. Each meeting has provided a further opportunity for identifying new areas of air pollution science demanding collaborative investigation.

The conference papers deal with a rich variety of topics. The presentation of case studies of specific regions and cities, including those in emerging countries are particularly encouraged.

## Conference Topics

Air pollution modelling

Monitoring and measuring

Air quality management

Indoor air pollution

Aerosols and particles

Emission studies

Air Pollution chemistry

Source identification

Global and regional studies

Exposure and health effects

Economics of air pollution control

Policy and legislation

Case studies

Innovative technologies

**CALL FOR PAPERS**

# AIR POLLUTION 2015

**23<sup>rd</sup> International Conference on Modelling, Monitoring and Management of Air Pollution**

**I – 3 June 2015**  
**València, Spain**

**Organised by**  
Wessex Institute, UK  
University of the West of England, UK

**Sponsored by**  
WIT Transactions on Ecology and the Environment  
The International Journal of Sustainable Development and Planning

[wessex.ac.uk/air2015](http://wessex.ac.uk/air2015)

**WESSEX INSTITUTE**  
ADVANCING INTERNATIONAL KNOWLEDGE TRANSFER

## Benefits of Attending

Conference Proceedings Papers presented at Air Pollution 2015 will be published by WIT Press in Volume 198 of WIT Transactions on Ecology and the Environment (ISSN: 1746-448X Digital ISSN: 1743-3541) WIT Press ensures maximum worldwide dissemination of your research through its own offices in Europe and the USA, and via its extensive international distribution network.

Delegates will have the choice of receiving the conference book as either hard cover or digital format on a USB flash drive. The USB flash drive will, in addition, contain papers from previous conferences in this series.

**Indexing and Archiving** Papers presented at Wessex Institute conferences are referenced by CrossRef and regularly appear in notable reviews, publications and databases, including referencing and abstracting services such as SCOPUS, Compendex, Thomson Reuters Web of Knowledge and ProQuest. All conference books are archived in the British Library and American Library of Congress.

**Digital Archive** All conference papers are archived online in the WIT eLibrary (<http://library.witpress.com>) where they are easily and permanently available to the international scientific community.

**Journal Papers** After the conference, presenters at Air Pollution 2015 will be invited to submit an enhanced version of their research for possible publication in the International Journal of Sustainable Development and Planning published by the Wessex Institute.

**Reviews** Abstracts and papers are reviewed by members of the International Scientific Advisory Committee and other experts.

**Open Access** Open Access allows for the full paper to be downloaded from the WIT eLibrary archives, offering maximum dissemination. Authors who choose this option will also receive complimentary access for one year to the entire WIT eLibrary.

**Networking** Participants can present their research and interact with experts from around the world, becoming part of a unique community.

**Reduced Fee for PhD Students** The Wessex Institute believes in the importance of encouraging PhD students to present and publish innovative research at their conferences. As a result, the Institute offers PhD students a much reduced conference fee.

## Conference Chairmen

**O Horbarth**  
University Leipzig, Germany  
**J Longhurst**  
University of the West of England, UK

**C A Brebbia**  
Wessex Institute, UK

## International Scientific Advisory Committee

**J Barnes**  
University of the West of England, UK  
**C Borrego**  
University of Aveiro, Portugal  
**M Kastek**  
Military University of Technology, Poland

**M Lopes**  
University of Aveiro, Portugal  
**S Pongpiachan**  
National Institute of Development Administration, Thailand

**C Trozzi**  
Techie Consulting srl, Italy  
**P Zannetti**  
EnviroComp Institute, USA

**Citations** When referencing papers presented at this conference please ensure that your citations refer to **Volume 198 of WIT Transactions on Ecology and the Environment** as this is the title under which papers appear in the indexing services.

